
GC 100 POLYESTER GELCOAT

Supplied by: W.P. NOTCUTT LIMITED

TELEPHONE: 01483 223311

HOMWOOD FARM, NEWARK LANE, TELEFAX: 01483 479594

RIPLEY, SURREY, GU23 6DJ, ENGLAND

SPECIFICATION

Colour	Pink
Specific Gravity at 25°C	1.21
Viscosity at 25°C	-
Styrene	30%
Shelf Life at 25°C	3 Months
Flash Point (Abel closed cup)	38°C

TYPICAL CURED PROPERTIES*

Hardness	40 (Barcol 934-1)
Tensile Strength	69 Mpa
Flexural Strength	117 Mpa
Flexural Modulus	3.6 Gpa
Heat Distortion Point	59°C
Gel time using 1% M50 Catalyst	10 Minutes @ 25°C

GC 100 is a pre-accelerated isophthalic polyester gelcoat resin. GC100 is designed for application by brush to provide thick, even films free from air and drainage. GC100 is a high quality resilient gelcoat and offers excellent weathering properties. GC100 can be easily pigmented using polyester colour pastes to provide decorative finishes.

GC 100 is approved by Lloyd's Register of Shipping for use in the manufacture of marine vessels.

*Determined according to B.S. 2782 Part and Test Method.