
PF 915 POLYESTER RESIN

Supplied by: W.P. NOTCUTT LIMITED
HOMEWOOD FARM, NEWARK LANE,
RIPLEY, SURREY, GU23 6DJ

TELEPHONE: 01483 223311
TELEFAX: 01483 479594

SPECIFICATION

Colour	White
Viscosity at 25°C	5 poise
Specific Gravity at 25°C	1.54
Non-volatile content	77%
Acid value	12mg KOH/g
Flash Point (Abel closed cup)	31°C

TYPICAL CURED PROPERTIES*

Hardness	55 (Barcol 934-1)
Tensile Strength	10 Mpa
Flexural Strength	44 Mpa
Heat Distortion Point	64°C
Gel Time using 1% M50 Catalyst	10 Minutes @ 25°C

PF 915 is a pre-accelerated, thixotropic, medium viscosity, filled polyester resin offering a very high level of fire retardance.

Laminates manufactured from **PF 195** comply with Class 1 of BS476 Part 7 and Class 0 Building Regulations.

PF 915 offers good pot-life with medium rate of cure and reduced drainage on inclined surfaces.

*Determined according to B.S. 2782 Part and Test Method.

DISCLAIMER: The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. Before using, user shall determine the suitability of the product for the intended use and user assumes all risk and liability whatsoever in connection therewith.

Supplied by:

W.P. NOTCUTT LTD, HOMEWOOD FARM, NEWARK LANE, RIPLEY, SURREY, GU23 6DJ
TELEPHONE: 01483 223311 TELEFAX: 01483 479594